

## BITUMEN R 115 / 15

	Specification	Test Method
Relative density at 25 °C, g/ml	1.00-1.06	ASTM D70
Penetration @ 25°C, 0.1 mm	10-20	ASTM D5
Softening Point (Ring and Ball),°C	110-120	ASTM D36
Ductility at 25°C cm, min	1.5	ASTM D113
Loss on heating % by mass	0.2	ASTM D6
Flash point ( Cleveland open Cup ),	200	ASTM D92
Solubility in toluene % wt min	99	EN 12592:2000