

BITUMEN R 90 / 15

| | Specification | Test Method |
|------------------------------------|----------------------|--------------------|
| Specific Gravity @ 25/25 °C | 1.05 approx. | D-70 |
| Penetration @ 25°C | 10/20 | D-5 |
| Softening Point C | 85/95 | D-36 |
| Ductility at 25°C | 3 min | D-113 |
| Loss on heating (wt)% | 0.2 max | D-6 |
| Flash point C | 225 max | D-92 |
| Solubility CS2 (wt)% | 99 min | D-4 |