

BITUMEN R 85 / 25

	Specification	Test Method
Specific Gravity @ 25/25 °C	1.05 approx	D-70
Penetration @ 25°C	20/30	D-5
Softening Point C	80/90	D-36
Ductility at 25°C	3 min	D-113
Loss on heating (wt)%	0.2 max	D-6
Flash point C	225 max	D-92
Solubility CS2 (wt)%	99 min	D-4