

## Bitumen PG 52-10

<b>Property</b>	<b>PG52</b>	<b>Test Method</b>
	<b>10</b>	
Average 7-day maximum pavement Design Temperature, °C	52	
minimum pavement Design Temperature, °C	> -10	
<b>Original Binder</b>		
Flash Point Temperature Minimum °C	230	AASHTO T48
Viscosity maximum 3 Pa.s, Test Temperature, °C	135	AASHTO T316
Dynamic Shear G*/sin minimum 2.2 KPa Test Temperature, °C	52	AASHTO T315
<b>Rolling Thin Film Oven Test</b>		
Mass change maximum percent	1	
Dynamic Shear G*/sin minimum 2.2 KPa Test Temperature, @ 10 rad/s °C	52	AASHTO T315
<b>Pressure Aging Vessel</b>		
PAV aging Temperature, °C	90	
Dynamic Shear G*/sin maximum 5000 KPa Test Temperature, @ 10 rad/s °C	25	AASHTO T315
Creep Stiffness S maximum 300 Mpa m-value minimum 0.300 Test Temperature, @ 60s °C	0	AASHTO T313
Direct Tension Failure strain minimum 1 % Test Temperature @ 1mm/min, °C	0	AASHTO T314
Critical low cracking Temperature Critical cracking determined by PP42 Test Temperature	0	AASHTO PP42