

## Bitumen PG 64-16

<b>Property</b>	<b>PG64</b>	<b>Test Method</b>
	<b>16</b>	
Average 7-day maximum pavement Design Temperature, °C	64	
minimum pavement Design Temperature, °C	> -16	
<b>Original Binder</b>		
Flash Point Temperature Minimum °C	230	AASHTO T48
Viscosity maximum 3 Pa.s, Test Temperature, °C	135	AASHTO T316
Dynamic Shear G*/sin minimum 2.2 KPa Test Temperature, °C	64	AASHTO T315
<b>Rolling Thin Film Oven Test</b>		
Mass change maximum percent	1	
Dynamic Shear G*/sin minimum 2.2 KPa Test Temperature, @ 10 rad/s °C	64	AASHTO T315
<b>Pressure Aging Vessel</b>		
PAV aging Temperature, °C	100	
Dynamic Shear G*/sin maximum 5000 KPa Test Temperature, @ 10 rad/s °C	28	AASHTO T315
Creep Stiffness S maximum 300 Mpa m-value minimum 0.300 Test Temperature, @ 60s °C	-6	AASHTO T313
Direct Tension Failure strain minimum 1 % Test Temperature @ 1mm/min, °C	-6	AASHTO T314
Critical low cracking Temperature Critical cracking determined by PP42 Test Temperature	-6	AASHTO PP42