

## Bitumen R 90-15

	<b>Specification</b>	<b>Test Method</b>
<b>Specific Gravity @ 25/25 °C</b>	1.05 approx.	D-70
<b>Penetration @ 25°C</b>	10/20	D-5
<b>Softening Point C</b>	85/95	D-36
<b>Ductility at 25°C</b>	3 min	D-113
<b>Loss on heating (wt)%</b>	0.2 max	D-6
<b>Flash point C</b>	225 max	D-92
<b>Soulubility CS2 (wt)%</b>	99 min	D-4